



Mirafi[®] RS380i

This is to certify that Mirafi[®] RS380i is a revolutionary geotextile created from super high-tenacity polypropylene filaments formed into an innovative weave to provide superior reinforcement strength and soil interaction integrated with high water flow and soil retention capabilities.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
STRENGTH			
Tensile Modulus @ 2% strain (CD)	ASTM D4595	lbs/ft (kN/m)	51000 (744)
HYDRAULIC			
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	75 (3056)
Permittivity	ASTM D4491	sec ⁻¹	0.9
SOIL RETENTION			
Apparent Opening Size (AOS) ¹	ASTM D4751	U.S. Sieve (mm)	40 (0.43)
Pore Size 0 ₉₅	ASTM D6767	microns	365 ³
Pore Size 0 ₅₀	ASTM D6767	microns	185 ³
SOIL INTERACTION			
Interaction Coefficient ²	ASTM D5321	--	0.89
Factory Seam Strength	ASTM D4884	lbs/ft (kN/m)	2700 (39.4)
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	80

¹ ASTM D4751: AOS is a Maximum Opening Diameter Value

² Interaction Coefficient value is for sand or gravel

³ Typical Values

Physical Properties	Unit	Typical Value
Roll Dimensions (width x length)	ft (m)	15 x 300 (4.5 x 91)
Roll Area	yd ² (m ²)	500 (418)
Estimated Roll Weight	lbs (kg)	328 (149)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2011 TenCate Geosynthetics North America
Mirafi[®] is a registered trademark of Nicolon Corporation